



Moldsil-15

High Performance Silicone Rubber for Mold making

Product Technical data sheet

PRODUCT DESCRIPTION

Moldsil-15 is a *premium* grade condensation curing type Silicone RTV, recommended for mold making applications. This is a flowable grade, having high mechanical strength and cures with various catalyst options (depending on the application requirements) at room temperature to a flexible elastomer, well suited for detailed and exact reproduction of artifacts, figures, architectural items and similar objects. **Moldsil-15** will reproduce the finest detail of the master and is suitable for a variety of art related and industrial applications such as mold making for reproducing prototypes, furniture, architectural items and sculptures.

Moldsil-15 can also be thickened with Thixopol 88 additive for *brush-on* type applications for reproducing vertical surfaces.

PRODUCT FEATURES

- Flowable type high strength silicone rubber curing at room temperature – Excellent detail reproduction
- Good mechanical properties - leading to long service life
- Highly elastic and excellent release properties – for easy de-molding
- Excellent chemical resistance – compatible with most molding materials with long service life
- Vertical surface replication with the use of a thixotropic additive Thixopol 88

APPLICATIONS

- ❑ **Moldsil-15** offers a good combination of good flow, high mechanical properties and excellent detail reproduction with good service life in mold making applications
- ❑ Moldsil-15 is compatible with several master materials such as wood, metal, plastics, rubber, clay...
- ❑ Molds made of Moldsil-15 can be used to cast a variety of reproduction materials such as polyester resins, polyurethanes low melt metal alloys, epoxies, wax, gypsum, clay, concrete
- ❑ Moldsil-15 is well suited for **pad printing** applications used in printing curved surfaces



TECHNICAL OVERVIEW

UNCURED PROPERTIES

PROPERTY	STANDARD	UNITS	VALUE
Colour			White
Viscosity Component A		m.Pa.s	20000
Specific Gravity	ASTM D-1475		1.15
Mixed Viscosity	ASTM D-2393	m.Pa.s	15000
Pot-life			
With 5% CAT-1	ASTM D-2471	Min.	100
With 5% CAT-9	ASTM D-2471	Min.	35
With 5% CAT-18	ASTM D-2471	Min.	15

CURED PROPERTIES* (With 5% CAT-9)

PROPERTY	STANDARD	UNITS	VALUE
Hardness	ASTM D-2240	Shore A	15
Tensile Strength	ASTM D-412	MPa	4
Elongation	ASTM D-412	%	500
Tear Strength	ASTM D-624	N/mm	18
Linear Shrinkage		(%)	<0.5

*Typical Properties, should not be used as specification

CATALYST OPTIONS

Moldsil-15 can be cured in to elastomeric products using the following cure options:

- ❑ **CAT-1** : General purpose catalyst with long work life for slow demolding
- ❑ **CAT-9** : Fast demolding catalyst with short work life for fast demolding
- ❑ **CAT-18** : Super Fast demolding catalyst with short work life for fast demolding

CATALYST PROPERTIES

PROPERTY	CAT-1	CAT-9
Colour	Transparent	Transparent
Density (g/cc)	0.95-0.97	0.95-0.97
Viscosity (m.Pa.s)	25	25
Mix Ratio (A:B)	100:5	100:5

METHOD OF USE

- ❑ **Surface Preparation:** The master surface should be clean, free of loose materials and dust particles. With porous substrates use a suitable release agent such as petroleum jelly or soap solution.
- ❑ **Mixing of Components:** Thoroughly stir Moldsil-15 before use, as filler separation might have occurred during prolonged storage. Select a container for mixing which is 4-5 times larger than the total material to be mixed. Weigh the A and B components in the desired ratio (ex: 100:5). Stir vigorously for several minutes scraping the sides and the bottom of the container to produce a homogeneous mix. Hand or mechanical (power) mixing can be used but do not mix for an extended period of time to avoid entrapping large amounts of air or causing over heating resulting in shorter work life.
- ❑ **De-aeration** : It is recommended that entrapped air be removed under vacuum to eliminate voids in the final product. This process will make the mixture to expand and then collapse. A volume increase of about 4-5 times will occur during the de-aeration process. Therefore, a large container should be used to accommodate this volume change. It should be also noted that prolonged application of vacuum

will remove the volatiles from the mixture that can result in poor cure.

- ❑ This system is sensitive to temperature and humidity and therefore can influence the cure speed. However, the final mechanical properties of the mold will be attained in one week. The material will cure to a flexible rubber within 24 hours at room temperature and the mold can then be separated from the master.
- ❑ **Pouring the Mix and Curing:** The mix should be poured as soon as possible on to the original master to avoid air entrapment. The material will cure at a speed depending on the selection and the amount of the catalyst.

HANDLING PRECAUTIONS AND SAFETY

Moldsil-15 contains constituents that have been found to be safe. Hence special handling precautions except general industrial hygiene need to be followed. Catalysts (CAT-1, CAT-9 and CAT-18) contain organo-tin compounds and are flammable and might cause irritation upon contact with eyes and skin. Adequate protective measures are recommended. Refer to Material safety Data Sheet (MSDS) for safe use of the product

USABLE LIFE AND STORAGE

The shelf life of Moldsil-15 and the catalysts (CAT-1 or CAT-9 or CAT-18) is 6 months from the date of manufacturing, if stored below 27° C in original unopened containers.

PACKING

Moldsil-15 is available in following kit forms :

1. Kit of 5.25 kg (5 kg Moldsil-15 + 250 grams of CAT-1 or CAT-9 or CAT-18)
2. Kit of 1.050 kg (1 kg Moldsil-15 + 50 grams of CAT-1 or CAT-9 or CAT-18)

LIMITATIONS

This product is neither tested nor claimed as suitable for food contact, medical or pharmaceutical applications.

Moldsil-15 is manufactured in India by :

Performance Polymers
9/11, 8th Cross, Ganesha Block,
Mahalakshmi Layout Bangalore 5600 096
Customer Care : Phone : +91-80-23499432
e-mail: ceo@performancepolymers.in

Limited Warranty : The information mentioned in this data sheet is a description of the product to the best of our knowledge. Recommendations for use do not constitute a warranty of the fitness for a particular use. It is the user's responsibility to thoroughly test the product in a particular application to determine its performance and safety.